

bis(difluoromethyl ether) and/or 1-difluoromethoxy-1, 1, 2, 2-tetrafluoroethyl difluoromethyl ether, said foaming agent compositions selected from the group consisting of:

	composition % by weight
I) difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); n-pentane	1-95 99-5
II) difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); iso-pentane	1-99 99-1
III) difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); dimethyl ketone (acetone)	1-60 99-40
IV) difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); 1,1,1,3,3-pentafluorobutane ($\text{CF}_3\text{CH}_2\text{CF}_2\text{CH}_3$, HFC 365 mfc)	1-99 99-1
V) difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); 1,1,1,4,4,4-hexafluorobutane ($\text{CF}_3\text{CH}_2\text{CH}_2\text{CF}_3$, HFC 356 ffa)	1-40 99-60
VI) difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); methoxymethyl methylether	1-96 99-14
VII) difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); n-hexane	30-99 70-1
VIII) 1-difluoromethoxy 1,1,2,2-tetrafluoroethyl	

	difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); n-pentane	1-93 99-7
IX)	1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); dimethyl ketone (acetone)	30-99 70-1
X)	1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); n-hexane	15-99 85-1
XI)	1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); ethyl alcohol	5-99 95-1
XII)	difluoromethoxy-bis (difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); 1,1,1,3,3-pentafluorobutane ($\text{CF}_3\text{CH}_2\text{CF}_2\text{CH}_3$, HFC 365 mfc) a hydrocarbon selected from n-pentane or isopentane	1-64 98-1 1-35 and
XIII)	difluoromethoxy-bis (difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); 1,1,1,4,4,4-hexafluorobutane ($\text{CF}_3\text{CH}_2\text{CH}_2\text{CF}_3$, HFC 356 ffa) a hydrocarbon selected from n-pentane or isopentane	1-22 98-43 1-35

wherein

(1) in the foaming agent compositions II, III, IV, V and VI, up to 40% by weight of the difluoromethoxy-bis(difluoromethyl ether) is optionally substituted with 1-difluoro methoxy-1,1,2,2-tetrafluoroethyldifluoromethyl ether;

(2) in the foaming agent composition IX, up to 40% by weight of 1-difluoromethoxy-1,1,2,2-tetrafluoroethyl difluoromethyl ether is optionally substituted by difluoromethoxy-bis(difluoromethyl) ether;

(3) in the foaming agent compositions I and VII, up to 50% by weight of difluoromethoxy-bis(difluoromethyl ether) is optionally substituted by 1-difluoromethoxy-1,1,2,2-tetrafluoroethyldifluoromethyl ether;

(4) in the foaming agent compositions VIII and X, up to 50% by weight of 1-difluoromethoxy-1,1,2,2-tetrafluoroethyldifluoromethyl ether is optionally substituted with difluoromethoxy-bis(difluoromethyl) ether.

2 (Amended). The process of claim 1, wherein said foaming agent compositions are selected from the group consisting of:

	composition % by weight
I) difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); n-pentane	25-95 75-5
II) difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); iso-pentane	25-98 75-2
III) difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); dimethyl ketone (acetone)	20-60 80-40
IV) difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); 1,1,1,3,3-pentafluorobutane ($\text{CF}_3\text{CH}_2\text{CF}_2\text{CH}_3$, HFC 365 mfc)	10-98 90-2

V)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$);	10-40
	1,1,1,4,4,4-hexafluorobutane ($\text{CF}_3\text{CH}_2\text{CH}_2\text{CF}_3$, HFC 356 ffa)	90-60
VI)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$);	25-96
	methoxymethyl methylether	75-14
VII)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$);	35-98
	n-hexane	65-2
VIII)	1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$);	25-93
	n-pentane	75-7
IX)	1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$);	50-98
	dimethyl ketone (acetone)	50-2
X)	1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$);	25-98
	n-hexane	75-2 and
XI)	1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$);	10-98
	ethyl alcohol	90-2.

12 (Amended). The process according to claim 1, wherein for polyurethane foams the compositions are selected from the group consisting of:

		composition % by weight
I)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); n-pentane	1-95 99-5
II)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); iso-pentane	1-99 99-1
IV)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); 1,1,1,3,3-pentafluorobutane ($\text{CF}_3\text{CH}_2\text{CF}_2\text{CH}_3$, HFC 365 mfc)	1-99 99-1
V)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); 1,1,1,4,4,4-hexafluorobutane ($\text{CF}_3\text{CH}_2\text{CH}_2\text{CF}_3$, HFC 356 ffa)	1-40 99-60
VI)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); methoxymethyl methylether	1-96 99-14
VII)	difluoromethoxy bis(difluoromethyl ether) ($\text{HCF}_2\text{OCF}_2\text{OCF}_2\text{H}$); n-hexane	30-99 70-1
VIII)	1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); n-pentane	1-93 99-7 and
X)	1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether ($\text{HCF}_2\text{OCF}_2\text{CF}_2\text{OCF}_2\text{H}$); n-hexane	15-99 85-1.

23 (Amended). Polyurethane polymer compositions comprising, as blowing agent substitutes of CFC-11 to give a homogenous foam having density of about 30 Kg/cm³, foaming agent azeotropic or nearly azeotropic compositions selected from the group consisting of:

	composition % by weight
I) difluoromethoxy bis(difluoromethyl ether) (HCF ₂ OCF ₂ OCF ₂ H); n-pentane	1-95 99-5
II) difluoromethoxy bis(difluoromethyl ether) (HCF ₂ OCF ₂ OCF ₂ H); iso-pentane	1-99 99-1
IV) difluoromethoxy bis(difluoromethyl ether) (HCF ₂ OCF ₂ OCF ₂ H); 1,1,1,3,3-pentafluorobutane (CF ₃ CH ₂ CF ₂ CH ₃ , HFC 365 mfc)	1-99 99-1
V) difluoromethoxy bis(difluoromethyl ether) (HCF ₂ OCF ₂ OCF ₂ H); 1,1,1,4,4,4-hexafluorobutane (CF ₃ CH ₂ CH ₂ CF ₃ , HFC 356 ffa)	1-40 99-60
VI) difluoromethoxy bis(difluoromethyl ether) (HCF ₂ OCF ₂ OCF ₂ H); methoxymethyl methylether	1-96 99-14
VII) difluoromethoxy bis(difluoromethyl ether) (HCF ₂ OCF ₂ OCF ₂ H); n-hexane	30-99 70-1 and
VIII) 1-difluoromethoxy 1,1,2,2-tetrafluoroethyl difluoromethyl ether (HCF ₂ OCF ₂ CF ₂ OCF ₂ H);	1-93